

## Nitrile Exam Gloves Powder Free, Standard Cuff



GloveOn® Reflex is the affordable alternative to vinyl gloves, and has been made in mind of aged care centres and hospitality. This nitrile glove conforms to the wearers hand and supports a greater level of barrier protection than vinyl gloves, reducing the risk of contamination in the workplace.

Distributed by:  
AMA Medical Products  
amamedicalproducts.com.au  
sales@amamedicalproducts.com.au  
1800 626 292



Physical Dimensions	
Length (mm)	≥ 230
Palm Thickness (mm)	≥ 0.05
Finger Thickness (mm)	0.08 ± 0.03
Physical Properties	
	Before Ageing
Force at Break (N)	≥ 18
Elongation at Break (%)	≥ 500
Inspection Levels & AQL	
	Inspection Level
Watertightness	G1
Physical Dimensions	S2
Physical Properties	S2
Visual Inspection (Major)	S4
Visual Inspection (Minor)	S4
Particulate Residue	N = 5

### REORDER CODE

NTR63SS SMALL  
NTR63MM MEDIUM  
NTR63LL LARGE  
NTR63XL X-LARGE

### FEATURES

- Fingertip textured • Powder free
- Not made with natural rubber latex
- Ambidextrous • Standard Cuff
- Translucent blue colour

### PACKAGING

200 gloves per box for S to L  
180 gloves per box for XL  
10 boxes per carton

### REGULATORY COMPLIANCE

ARTG 164563, FDA 510(k),  
REACH, ROHS Directive 2002/95/EC,  
EU 10/2011, EC 1935/2004,  
EU 2016/425

### STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124,  
ASTM D6978, EN ISO 374-1 (Type C),  
EN 16523-1, EN 374 part 2, 4 & 5,  
EN 420, EN 455 part 1, 2 & 3, EN 1186,  
EN 13130, CEN/TS 14234,  
ISO 10993 part 5 & 10, HACCP Certified

### MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 136419)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	13.4 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Tospor), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	14.4 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

**WARNING:** Carmustine and Thiotepa, at the tested concentration, degraded nitrile glove at 13.4 minutes and 14.4 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Chemical	EN 16523-1:2015 Permeation Level	EN 374-4:2013 Mean Degradation (%)
K 40% Sodium Hydroxide	6	-9.5
T 37% Formaldehyde	4	16.1