



Latex Exam Gloves Powder Free, Standard Cuff

Just like this pioneer, GloveOn® Ridley has also conquered many different market segments. It continues to be the most popular choice of powder free latex glove in our range, offering unquantifiable aqueous latex proteins, low protein, and non-sensitising and non-irritant properties.

Distributed by:
AMA Medical Products
amamedicalproducts.com.au
sales@amamedicalproducts.com.au
1800 626 292



Physical Dimensions

| | |
|-----------------------|-------------|
| Length (mm) | ≥ 230 |
| Palm Thickness (mm) | 0.13 ± 0.03 |
| Finger Thickness (mm) | 0.14 ± 0.03 |

Physical Properties

| | Before Ageing | After Ageing |
|------------------------|---------------|--------------|
| Tensile Strength (MPa) | ≥ 18 | ≥ 16 |
| Elongation (%) | ≥ 650 | ≥ 500 |

Inspection Levels & AQL

| | Inspection Level | AQL |
|---------------------------|------------------|-------------|
| Watertightness | G1 | 1.5 |
| Physical Dimensions | S2 | 4.0 |
| Tensile Strength | S2 | 4.0 |
| Visual Inspection (Major) | S4 | 2.5 |
| Visual Inspection (Minor) | S4 | 4.0 |
| Particulate Residue | N = 5 | ≤ 2mg/glove |
| Protein Content | N = 3 | ≤ 50µg/g |

*Full test reports on Sensitisation Testing, Primary Skin Irritation and Residual Proteins Testing are available upon request.

REORDER CODE

| | |
|---------|---------|
| CHL11XS | X-SMALL |
| CHL11SS | SMALL |
| CHL11MM | MEDIUM |
| CHL11LL | LARGE |
| CHL11XL | X-LARGE |

FEATURES

- Fully textured • Powder free
- Made with natural rubber latex
- Protein level ≤ 50µg/g
- Ambidextrous • Standard cuff
- Natural colour

PACKAGING

100 gloves per box for XS to XL
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 127794, FDA 510(k), REACH,
EC 1935/2004, CMDR SOR-98-282,
EU 2016/425, MDD 93/42/EEC

STANDARDS

AS/NZS 4011-1, ISO 11193-1, ASTM D5151,
ASTM D3578, ASTM D6124, ASTM D5712,
EN ISO 374-1 (Type B), EN 16523-1,
EN 374 part 2, 4 & 5, EN 420,
EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130,
CEN/TS 14234, ISO 10993 part 5 & 10,
HACCP Certified

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

| Measured breakthrough time (minutes) | >10 | >30 | >60 | >120 | >240 | >480 |
|--------------------------------------|-----|-----|-----|------|------|------|
| Permeation performance level | 1 | 2 | 3 | 4 | 5 | 6 |

| Chemical | EN 16523-1:2015 Permeation Level | EN 374-4:2013 Mean Degradation (%) |
|-------------------------|----------------------------------|------------------------------------|
| K 40% Sodium Hydroxide | 3 | -24.7 |
| P 30% Hydrogen Peroxide | 4 | 19.8 |
| T 37% Formaldehyde | 5 | -23.1 |